Contribution to the FEM simulation of Ti6Al4V Machining

Marek Vrabel^{1,*}, Numan Durakbasa², Pavel Kovač³ and Ildikó Maňková⁴

¹ Technical University of Košice, Faculty of Mechanical Engineering, Department of Manufacturing Technology and Materials, Mäsiarska 74, 040 01 Košice, Slovakia

² Institute for Production Engineering and Laser Technology, Vienna University of Technology, Getreidemarkt 9, 1060 Wien, Austria

³ Faculty of Technical Sciences, Dositeja Obradovića 6, 21000 Novi Sad, Serbia

⁴ Technical University of Košice, Faculty of Mechanical Engineering, Department of Computer Support of Technology, Mäsiarska 74, 040 01 Košice, Slovakia

Abstract: The paper briefly reviews current scientific publications related to machining of difficult to cut materials and finite element modelling methods (FEM) applied in various chip making processes. Simulations of the orthogonal machining process with regard to define optimal cutting parameters as well as cutting wedge geometry in hole making TiAlN alloy was performed according to test plan based on design of experiment (DoE) methodology. The numerical simulations were performed using commercial finite element software (AdvantEdge), which is suitable to solve complex thermo-mechanical problems occurring in cutting zone during chip making process. A Lagrangian finite element-based model is applied within simulation procedure. Results from experimental simulation were evaluated by main effect and surface response plots.

Keywords: Design of experiment (DoE); finite element method (FEM); response surface methodology (RSM); titanium alloys; tool geometry.

1. Introduction

In modern manufacturing industry it is essential to produce under low costs and high quality of products in a short time. It is well known that cutting tools are subjected to high stresses by modern machining technologies, like dry machining, high-speed machining or high-performance machining [1]. Moreover, the requirements in quality of the finished product, decrease of costs, flexibility, reduced times of production, productivity, capacity to process new materials and miniaturization are among others. [2], [3]. High material removal rate, high cutting parameters requires high tool performance. Therefore, the geometry of the cutting edge, and its preparation, play a significant role on the performance of a cutting tool when machining widely used or difficult-to-machine materials [4], [5]. Ti6Al4V titanium alloy is often used not only in the aircraft industry due to the good compromise between mechanical resistance and tenacity, together with its low density and excellent corrosion resistance. However, this material is known to be difficult to machine. One of the reasons is due to its low thermal conductivity which gives rise to high pressures and temperatures at the tool-chip interface, a plastic instability localized in adiabatic shear bands, tool wear by thermal fatigue and diffusion. [6], [7], [8]. In order to increase productivity and tool life in the machining of titanium alloys, it is necessary to develop a reliable FE model for conventional

* Corresponding author: Marek Vrabel, Phone: +421-55-602-3523
E-mail address: marek.vrabel@tuke.sk

cutting speed regime. To accurately analyze this process using numerical methods such as Finite Element Analysis (FEA) the knowledge of material constitutive behaviour under these severe loading conditions is a pre-requisite. Finite element analysis is preferred than the laborious experimental work in order to save time and cost. Researchers have previously concluded that the results obtained from finite element analysis stays close to the experimental results. Kumar [8] concluded that, as the included angle between the cutting edges decreases, the wear depth and cutting forces are getting reduced. i. e. when the shape is changed from 90° to 55°. Sasahara et al. [9] used finite element method to develop a process model and investigated the effects of corner radius and feed rates in a face turning process. Their results showed

that residual stresses changed from tension to compression as feed rate decreases and as the corner radius become smaller. Yung-Chang Yen et al. [10] has shown how various tool geometries like round/hone edge and T-land/chamfer edge affects process variables, while machining AISI 1020 by uncoated cemented carbide using FEM cutting simulation. Matsumura et al. [11] presented hybrid simulation of drilling to save the time for analysis. In the hybrid simulation, the FE analysis is conducted in a 2D model determined by the energy analysis for the cutting force prediction as well as for surface quality. Selected results of experimental and simulation processes for cutting forces are illustrated in Table 1 when machining titanium alloy Ti6Al4V.

This paper presents the application of Finite

Table 1: State of the art of experimental and simulation data for cutting forces and temperature when machining titanium alloy Ti-6Al-4V.

Author	Tool material	Tool geometry [°]	Cutting Conditions	Exp. Fx [N]	Sim. Fx [N]	Exp. Fy [N]	Sim. Fy [N]	Sim. T [°C]
Calamaz et al. 2008 [6]	Uncoated carbide	$\gamma = -4, \alpha = 7$ $r_n = 20 \text{ } [\mu\text{m}]$	$v_c = 180\text{m/min}$ $f = 0,1 \text{ mm}$	-	-	550	300	700
Ulutun et al. 2013 [12]	Uncoated carbide	$\gamma = -5$ $r_n = 20 \text{ } [\mu\text{m}]$	$v_c = 120\text{m/min}$ $a_p = 5 \text{ mm}$	240	245	495	520	-
Weyn et al. 2010 [13]	Uncoated carbide	$\gamma = -10, \alpha = 8$ $r_n = 10 \text{ } [\mu\text{m}]$	$v_c = 120\text{m/min}$ $f = 0,06 \text{ mm}$	40	-	120	-	
Constantin et al. 2012 [14]	Uncoated carbide	$\gamma = 0, \alpha = 11$ $r_n = 10 \text{ } [\mu\text{m}]$	$v_c = 150\text{m/min}$ $f = 0,1 \text{ mm}$	-	225	-	100	450
Özel. et al. 2010 [15]	Uncoated carbide	$\alpha = 11, \gamma = -5$ $r_n = 5 \text{ } [\mu\text{m}]$	$v_c = 100\text{m/min}$ $a_p = 2 \text{ mm}$	380	229	750	590	785
Lazoglu et all 2016 [16]	Uncoated carbide	Twist drill	$v_c = 10\text{m/min}$ $f = 0,1 \text{ mm}$					370
			$v_c = 30\text{m/min}$ $f = 0,2 \text{ mm}$					550

Element Method (FEM) to study the effect of tool geometry and cutting conditions of uncoated carbide cutting tool WC/Co (rake angle, cutting edge radius) on cutting force (Fx, Fy) and temperature (T) in the orthogonal machining process of titanium alloy Ti6Al4V, under dry cutting conditions when using machining parameter variables cutting speed and feed.

2. Experimental Setup and Simulation Methodology of AdvantEdge

One of the important parameters in the

orthogonal metal cutting process is the rake angle between the face of the cutting tool and the plane perpendicular to the cutting direction [9]. The effect of cutting edge radius and rake angle on the cutting force and temperature has been studied. A Lagrangian finite element-based model is applied in the simulation of cutting forces and temperature in two-dimensional orthogonal metal cutting of titanium Ti6Al4V alloy. Chemical composition of the titanium alloy is listed in Table 2.

The simulations were performed using Third Wave AdvantEdge Systems software. The cutting

Table 2: Chemical composition of Ti6Al4V.

Material	Ti	Al	V	Fe	O	C	N
Ti-6Al-4V (%)	Balance	6.01	3.87	0.18	0.14	0.009	0.006

Table 3: Simulation input parameters.

Parameter		Symbol	Unit	Value
Work piece Ti6Al4V	Workpiece length	lw	[mm]	5,0
	Workpiece height	hw	[mm]	2,0
Tool Carbide-Grade-K (WC)	Rake angle	γ	[°]	5; 10; 15
	Rake length	ly	[mm]	2,0
	Relief angle	α	[°]	10
	Relief length	la	[mm]	2,0
	Cutting Edge Radius	rn	[μ m]	20; 50; 80
	Min. Tool Element Size	-	[mm]	0,02
	Max. Tool Element Size	-	[mm]	0,1
	Mesh Grading	-	-	0,4
Process Orthogonal cutting	Depth of cut	doc	[mm]	1,0
	Length of cut	loc	[mm]	3,0
	Feed	f	[mm]	0,05; 0,1; 0,15
	Cutting speed	vc	[m/min]	30; 90; 120
	Initial temperature	T	[°]	20
	Friction coefficient	μ	-	0,5

Table 4: Initial machining parameters.

Factors	Symbol	Unit	Cutting conditions		
			Level 1	Level 2	Level 3
Cutting speed	vc	[m/min]	30	90	120
Feed	f	[mm/rev]	0,05	0,10	0,15
Cutting edge radius	rn	[μ m]	20	50	80
Rake angle	γ	[°]	-5	-10	-15

Table 5: Taguchi orthogonal array design L9 with simulation output characteristics.

Exp	Cutting speed vc [m/min]	Feed f [mm]	Cutting edge radius rn [μ m]	Rake angle γ [°]	Feed force Fx [N]	Cutting force Fy [N]	Temp. T [°C]
1	30	0,05	20	-5	130	109	452
2	30	0,10	50	-10	220	184	523
3	30	0,15	80	-15	290	246	573
4	90	0,05	50	-15	125	165	679
5	90	0,10	80	-5	235	271	822
6	90	0,15	20	-10	251	121	862
7	120	0,05	80	-10	146	256	925
8	120	0,10	20	-15	174	97	869
9	120	0,15	50	-5	271	199	1065

tool material employed was cemented carbide grade K (WC/Co). The initial temperature for the work piece and tool is set as 20°C (room temperature). Coefficient of friction was set to 0.5 by default. Machining parameters (cutting speed and feed), and cutting tool geometry (rake angle and cutting edge radius) were considered as variables. Machining parameter such as clearance angle (α) and depth of cut (doc) were kept constant at 10° and 1 mm, respectively. The input values to simulation process are given in Tab. 3.

Design of experiment (DoE) is a powerful statistical method for determining the unknown properties of the machining parameters in the experiment process and for analyzing and modeling the interaction among the factors. Taguchi method also allows controlling the variations caused by the uncontrollable factors which are not taken into consideration at conventional design of experiment [8], [17], [18].

In this study, machining experiments are planned using Taguchi L9 (3⁴) orthogonal array with output characteristics of cutting forces F_x and F_y and temperature T which were obtained by means of FEM simulations listed in Table 5. Experimental tests are conducted by considering four machining parameters: cutting speed, feed, cutting edge radius and rake angle at three levels as shown in Table 4.

3. Results and Discussion

Analysis of simulation output parameters was performed in Tecplot 360 software. Statistical software Minitab 16 and Matlab R2012 was employed to process and evaluate of experimental data. The experimental results based on the orthogonal array are then transformed into analysis of the Main effect of means to evaluate the performance characteristics. Finally, the desirability function approach is used in the optimization of multiple-response surfaces through RSM method.

Values of cutting forces in X and Y directions and temperature were obtained at varying cutting conditions as listed in Table 4. Fig. 1 shows the plots of feed force F_x and cutting force F_y of Exp. 3 and Exp. 5, respectively. The maximum achieved feed force and cutting force were approximately 290 N and 271 N, at Exp. 3 and Exp. 5, respectively. Fig. 2 shows the temperature distribution on tool edge of Exp. 3 and Exp. 5, respectively. The maximum

achieved temperature were approximately 1065°C at Exp. 9. The largest peak temperature achieved in Exp. 9, it is attributed to adjusting cutting speed $v_c = 120$ m/min and feed $f = 0.15$ mm, which represents the highest value.

Fig. 1: Cutting Force (F_x , F_y) as a function of length of cut: (a) Exp. 3, (b) Exp. 5.

Fig. 2: Temperature (T) as a function of length of cut: (a) Exp. 3, (b) Exp. 5.

3.1 Analysis and evaluation of results using Taguchi design

The values of the significant factors for feed force F_x , cutting force F_y and temperature T were given in the Table 6, 7 and 8 and Fig. 3 can be used to estimate the mean cutting force and temperature with optimal performance conditions. Two factors were found to be significant in both F_x and F_y for Response table for Means analysis that is feed and cutting edge radius, which gave the smallest cutting forces values. Two factors were found to be significant in temperature T for Response table for Means analysis that is cutting speed and feed, which gave the smallest temperature values. To determine the interaction effects of machining parameters on cutting forces and temperature, the individual

Table 6: Taguchi orthogonal array design L_9 with simulation output characteristics

Level	Cutting speed v_c [m/min]	Feed f [mm]	Cutting edge radius r_n [μ m]	Rake angle γ [$^\circ$]
1	230,3	138,7	198,3	209,7
2	216	222,3	214	221,7
3	207	292,3	241	222
Delta	23,3	153,7	42,7	12,3
Rank	3	1	2	4

Table 7: Response table for Means for feed force F_x .

Level	Cutting speed v_c [m/min]	Feed f [mm]	Cutting edge radius r_n [μ m]	Rake angle γ [$^\circ$]
1	196,7	181	117,7	183,7
2	192,7	191	191	196,7
3	191	208,3	271,7	200
Delta	5,7	27,3	154	16,3
Rank	4	2	1	3

Table 8: Response table for Means for cutting force F_y .

Level	Cutting speed v_c [m/min]	Feed f [mm]	Cutting edge radius r_n [μ m]	Rake angle γ [$^\circ$]
1	516	685,3	727,7	707
2	787,7	738	755,7	770
3	953	833,3	773,3	779,7
Delta	437	148	45,7	72,7
Rank	1	2	4	3

Fig. 3: Main effect plot for Means of feed and cutting forces (a) (F_x). (b) (F_y).

input parameters were ranked. Response table for Means and ranked factors for cutting force F_x and F_y and temperature T are listed in Table 6, 7 and 8, respectively. The presented values (Table 6, 7 and 8) show the Means at each level of the control factors and how it is changed when settings of each control factor are changed from one level to another. Based on Taguchi prediction the smallest values of Means

have more significant effect on cutting forces F_x , F_y and T , respectively.

When feed force F_x is considered, from Tab. 6, the feed is listed to have a strong effect on feed force F_x . The second significant parameter is cutting edge radius. The other two examined parameters like cutting speed and rake angle have no significant effect on feed force. From the response table for

means analysis, the optimal cutting parameters for feed force F_x were determined as $f_1 = 0,05$ mm, $r_{n1} = 20$ μ m, $v_{c3} = 120$ m/min and $\gamma_1 = -15^\circ$, respectively.

When cutting force F_y is considered, from Tab. 7, the cutting edge radius is listed to have a strong effect on cutting force F_y . The second significant parameter is feed. The other two examined parameters like rake angle and cutting speed have no significant effect on cutting force. From the response table for means analysis, the optimal cutting parameters for cutting force F_y were determined as $r_{n1} = 20$ μ m, $f_1 = 0,05$ mm. $v_{c3} = 120$ m/min and $\gamma_1 = -15^\circ$, respectively.

When temperature T is considered, from Tab. 8, the cutting speed is listed to have a strong effect on temperature T . The second significant parameter is feed. The other two examined parameters rake angle and cutting edge radius have no significant effect on temperature. The optimal cutting parameters for temperature T were determined as $v_{c1} = 30$ m/min, $f_1 = 0,05$ mm, $\gamma_1 = -15^\circ$ and $r_{n1} = 20$ μ m, respectively.

Fig.3 shows the main effect plot for Means of cutting forces F_x , F_y and Temperature T , respectively. Main effect plot for Means (Smaller is Better) shows the sharply slope towards to the biggest value at feed and cutting edge radius, which have the most significant effect on feed force F_x and cutting force F_y , respectively. The results further indicate that increasing of feed increases the feed force F_x while for cutting force F_y increases with increasing cutting edge radius. However, cutting speed and rake angle has no significant effect on the cutting force F_x and F_y .

Fig. 4: Main effect plot for Means of temperature (T).

Fig.4 shows sharply slope towards to the biggest value at cutting speed, which have the most significant effect on temperature T . The second

significant parameter is feed. Note that cutting edge radius and rake angle has no significant effect on temperature T .

The 3D response surface plots for feed force F_x , cutting force F_y and temperature T are shown on Fig.5. As the model is adequate these 3D surface plots can be used for estimating the cutting force and temperature for the any suitable combination of the input parameters namely cutting speed, feed, cutting edge radius and rake angle.

Fig. 5: The 3D response surface plots of feed force (F_x) cutting force (F_y) and temperature (T) vs. cutting edge radius (r_n) and feed (f).

It is clear from Fig. 5 that the feed force F_x decreases with decreasing cutting edge radius. Minimal values of feed force F_x can be obtained with a smaller feed, and cutting edge radius has smaller significant effect on feed force F_x . Results revealed that smaller value of cutting edge radius decreases value of cutting force F_y , while the cutting edge radius has the most significant effect and feed has smaller significant effect on cutting force F_y . The results further indicate that increasing of cutting speed increasing the temperature T , while the feed has less significant effect on temperature T are shown in Fig. 5.

4. Conclusions

This paper focuses on Taguchi method and response surface methodology (RSM) for investigating of influence of the cutting parameters on the cutting forces and temperature when orthogonal cutting of titanium alloy Ti6Al4V. In the simulation, different cutting speed, feed, cutting edge radius and rake angle values are used. Results were evaluated using the analysis of main effect graphs of means (smaller is better). Optimal operating parameters are determined using the Taguchi method, RSM function. The results can be drawn as follows:

■ *The simulation results were analyzed using main effect graphs of means. For the feed force F_x , the feed is the main influencing factor, and cutting edge radius is the second. However, for the cutting force F_y , the cutting edge radius is the main influencing factor and feed is the second influencing factor, followed by the cutting speed and rake angle. Cutting speed has no significant effect on the cutting forces.*

■ *Response surface optimization shows that the optimal combination of machining parameters is for cutting speed 30 m/min, feed 0,05 mm, cutting edge radius 20 μ m and rake angle -15°, respectively. From the analysis results, the optimization values were obtained as 123.67 N, 98.67 N, and 379.33°C for the F_x , F_y and T , respectively. Hence, RSM can better predict the effect of parameters on results and is a better method for optimization.*

■ *In the desirability function approach, the values of composite desirability were 1.0 and 1.0 for RSM model of F_x , F_y and T , respectively. Desirability function in the RSM method for the optimization of response is a very powerful tool for predicting cutting forces. For the reason that, the value of composite desirability is 1,000000, which representing functional statistical significance is 100 %.*

5. Acknowledgements

This work was supported by the Slovak Research and Development Agency bilateral project under the contract SK-AT-2015-0020 Integration of Nanometrological Process into Quality Assessment for Small Diameter of End Mill Cutters and the bilateral project APVV SK-SRB-2016-0045 Integration of artificial intelligence methods into innovative milling processes.

6. References

- [1] RODRIGUEZ C.J.C.: Cutting edge preparation of precision cutting tools by applying micro-abrasive jet machining and brushing. Kassel University press GMBH. (2009) 189.
- [2] RECH J. et al.: Influence of cutting edge radius on the wear resistance of PM-HSS milling inserts. (2005), Wear, vol. 259, pp. 1168-1176.
- [3] DENKENA B. et al.: Effects of the cutting edge micro geometry on tool wear and its thermo-mechanical load. (2011), CIRP Journal of Manufacturing Science and Technology, Vol. 60 73–6.
- [4] WYEN C.-F. et al.: Influence of cutting edge radius on cutting forces in machining titanium. (2010), CIRP-Man. Technology, vol. 59, pp. 93–96.
- [5] BASSETT E. et al.: On the honed cutting edge and its side effects during orthogonal turning operations of AISI1045 with coated WC-Co inserts. (2012), CIRP J of Man. Scien and Technology, vol. 5, pp. 108–126.
- [6] CALAMAZ M. et al.: A new material model for 2D numerical simulation of serrated chip formation when machining titanium alloy Ti–6Al–4V. (2008), Int. J of Machine Tools & Manufacture vol. 48 pp. 275–288.
- [7] UMBRELLO D.: Finite element simulation of conventional and high speed machining of Ti6Al4V alloy. (2008), Journal Of Materials Processing Technology vol. 196, pp. 79–87.
- [8] KUMAR N.S. et al.: Finite element analysis and optimization of uncoated carbide cutting inserts of different tool geometries in machining AISI 1045 steel. Journal of Mech. Sciens, Vol. 1 No. 1, pp 37–47.
- [9] SASAHARA H. et al.: Prediction model of surface residual stress within a machined surface by combining two orthogonal plane models. (2004), Int. JI of Machine Tools and Manufacture, vol. 44, pp. 815–822.
- [10] YEN Y. CH.: A finite element analysis of orthogonal machining using different tool edge geometries”, (2002), Journal of materials processing technology, vol. 146, pp. 72–81.
- [11] MATSUMURA T., TAMURA Sh.: Cutting simulation of titanium alloy drilling with energy analysis and FEM (2015) Proceedia CIRP 31 pp.252 – 257
- [12] ULUTAN D. et al.: Determination of Tool Friction in Presence of Flank Wear and Stress Distribution Based Validation using Finite Element Simulations in Machining of Titanium and Nickel Based Alloys. (2013), J of Materials Processing Technology pp. 1 – 43.
- [13] WYEN C.F. et al.: Influence of cutting edge radius on cutting forces in machining titanium. (2010), CIRP – Man. Technology vol. 59, pp. 93–96.
- [14] CONSTANTIN C et al.: FEM tools for cutting process modelling and simulation. (2012), U.P.B. Sci. Bull., Series D, vol. 74, ISSN 1454-2358.
- [15] ÖZEL T. et al.: Investigations on the effects of multi-layered coated inserts in machining Ti6Al4V alloy with experiments and finite element simulations. (2010), CIRP Manufacturing Technology vol. 59, pp. 77.
- [16] LAZOGLU I, et al. Thermal analysis in Ti-6Al-4V drilling. CIRP Annals - Manufacturing Technology (2017), <http://dx.doi.org/10.1016/j.cirp.2017.04.020>
- [17] MADADIA A.J. et al.: Optimisation of machining parameters for turning operations based on response surface method-

ology. (2013), Measurement vol. 46, pp. 1521 – 1529.

- [18] SARIKAYA M. et al.: Taguchi design and response surface methodology based analysis of machining parameters in CNC turning under MQL. (2013), Journal of Cleaner Production, pp. 1 – 40.

Biographical notes

Marek Vrabel', Ing., Ph.D., born 16th July 1985 in Prešov; graduated from Technical University of Košice, Faculty of Mechanical Engineering in the field of machining technology, in 2009. Position: Research fellow, Department of Manufacturing Technology and Materials; Specialization: Machining operations, Cutting tools, and Process Monitoring. Participated in several projects with national as well as international consortium. Attended several internships and short term visits all over the Europe (Sweden, Germany, Spain, UK a.o). Author and co-author of several publications in scientific databases (Current Contents, Scopus, WOS).

M. N. Durakbasa, Professor Dipl. Ing. Dr. techn. Prof. h.c. Dr. h.c., born: 21th May 1955 in K. Maras (TR). Experience in Quality Management Methods and Quality Engineering. Publications: 8 books, more than 320 scientific papers. More than 280 lectures in various European countries as well as in USA, Azerbaijan, Brazil, China, Cuba, Egypt, Japan, Kirghizstan, Korea, VAR and Turkey.

Pavel Kovač, Prof., Ing. Dr., field of interest: Machining, Process monitoring, Virtual instrumentation, DoE, Sensor development, Artificial intelligence. Visiting professor on Prince of Songkla University in Hatyai, Thailand (2006). Principal investigator of two Serbian national projects number TR14206 and TR35015. Participant in Serbian national projects number TR3203 and TR14030 and CEEPUS projects CII-SK-0405-02-1011, CII-SK-0067-06-1011, CII-PL-0007-06-1011.

Ildikó Maňková, Prof., Ing., CSc., graduated from Technical University of Košice, Faculty of Mechanical Engineering (1976), PhD thesis (1984), habilitation (1994), professor in the field of Manufacturing Technology and Materials (2005), Professor honoris causae Facultatis Mechanicae Universitatis Miskolc Hungary (2010). Research on procedures and ways of process and tool condition monitoring, studies in surface roughness in hard and precision machining, research on ceramic cutting insert and coated cutting carbide inserts wear behaviour and tool performance, application of statistical methods in measured data processing.